

## GHISA GRIGIA

ČSN	ČSN EN 1561	DIN 1691	UNI 5007	Resistenza alla trazione Rm [Mpa]	Durezza [HB]
422415	EN-GJL-150	GG-15	G15	>150	140-190
422420	EN-GJL-200	GG-20	G20	>200	150-230
422425	EN-GJL-250	GG-25	G25	>250	180-250
422430	EN-GJL-300	GG-30	G30	>300	200-275
422435	EN-GJL-350	GG-35	G35	>350	220-290

ČSN	Durezza dipendente sullo spessore della parete del getto [HB]			
	10 - 15 mm	15 - 30 mm	30 - 45 mm	45 - 80 mm
422415	150 - 210	140 - 200	130 - 190	120 - 180
422420	180 - 240	160 - 220	150 - 210	140 - 200
422425	200 - 260	180 - 240	170 - 230	160 - 220
422430	220 - 280	200 - 260	190 - 250	180 - 240
422435	230 - 290	210 - 270	200 - 260	190 - 250

## GHISA SFEROIDALE

ČSN	ČSN EN 1563	DIN 1693	UNI 4544	Limite dello scorrimento Rp 0,2 [Mpa]	Resistenza alla trazione Rm [Mpa]	Duttilità Amin [%]
422314	EN-GJS-400-18LT	GGG-40.3	-	>240	>400	18
422304	EN-GJS-400-18	GGG-40	GS 400-12	>250	>400	15
422305	EN-GJS-500-7	GGG-50	GS 500-7	>320	>500	7
422306	EN-GJS-600-3	GGG-60	GS 600-3	>380	>600	3
422307	EN-GJS-700-2	GGG-70	GS 700-2	>440	>700	2